International Journal of Enhanced Research in Medicines & Dental Care (IJERMDC),
ISSN: 2349-1590, Vol. 13 Issue 10, October 2026

Implant Screw Biomechanics: A Narrative Review of Mechanical Principles, Joint Stability, Complications and Preventive Strategies

Dr. Mitali Niras[1], Dr. Tamanna Chhabra[2], Dr. Yogesh Chaudhari[3], Dr. Purvi Ganeriwal[4]

[1,2,3,4]K.M Shah Dental College and Hospital, Piparia, Waghodia, Vadodara Gujarat

ABSTRACT

Background: The long-term performance of implant-supported prostheses depends partly on the integrity of the screw joint, the distribution of occlusal forces and the maintenance of preload.

Objective: To review the biomechanical principles governing implant screws, the factors associated with loosening and fracture, and strategies described for improving joint stability.

Methods: This narrative review synthesizes the supplied educational presentation on implant screw biomechanics and uses only the publications listed within that presentation. No systematic database search or independent critical appraisal was performed.

Review findings: Applied torque produces elastic screw elongation, preload and a clamping force that resists joint separation. Friction, embedment relaxation, screw material, implant connection design, nonaxial loading, cantilevers and prosthetic configuration modify joint stability. Screw loosening and fracture are important mechanical complications. The presentation emphasizes manufacturer-specified torque, retightening after settling, reduction of unfavorable loading and prompt management of loosened components.

Conclusion: Screw-joint stability requires both adequate preload and control of separating forces. Clinical recommendations must be interpreted in relation to the specific implant system and the limitations of the source material.

Keywords: Dental implant; abutment screw; biomechanics; preload; screw loosening; settling effect; torque; screw fracture.

INTRODUCTION

Implant-supported rehabilitation provides a restorative option for partially and completely edentulous patients, but biological and mechanical complications remain possible. The abutment screw connects implant components and contributes to the integrity of the prosthetic assembly. Loss of joint stability may compromise the restoration and necessitate repeated clinical intervention. The source presentation identifies screw loosening as a prominent concern, particularly for single-unit restorations. [3,10]

The mechanical behavior of the joint cannot be considered separately from occlusal loading, prosthetic geometry and material properties. This review organizes the concepts presented in the source slides into a clinically oriented account of force transmission, torque and preload, friction, screw strength, connection design, failure mechanisms and prevention. [6,10]

SCOPE AND APPROACH

This is a narrative synthesis of the 53-slide presentation “Implant Screw Biomechanics.” The supplied Word file was consulted only as a structural example and supplied no data, wording, figures or references. Bibliographic entries below are

restricted to references explicitly listed in the presentation. Citations identify thematically relevant sources; the slides do not provide a complete study-by-study evidence map for every assertion. Consequently, numerical estimates without a clearly attributable primary study are described cautiously rather than presented as independently verified pooled findings.

FUNDAMENTAL BIOMECHANICAL PRINCIPLES

Forces acting on implant-supported restorations

Dental implants are exposed to functional occlusal loads that vary in magnitude, direction, frequency and duration. Parafunction may add repeated and oblique loading; the tongue and circumoral musculature can also exert relatively small horizontal forces. Three clinically relevant axes—mesiodistal, faciolingual and occlusoapical—allow complex forces to be resolved into components. Because contact forces are seldom perfectly axial, their direction influences the stresses experienced by the implant, prosthetic components and surrounding bone. [5,6]

The presentation distinguishes compression, tension and shear. Compressive loading tends to bring structures together, whereas tensile forces separate them and shear forces promote sliding at an interface. The slides describe cortical bone as better adapted to compression than shear and therefore emphasize prosthetic designs that reduce unfavorable transverse loading. These descriptions are biomechanical principles rather than patient-level comparative outcome estimates. [6]

Implant dimensions, thread form and bending moments

Implant diameter and thread geometry influence the distribution of mechanical stress. The presentation describes wider implants as distributing forces over a larger area, while narrow designs may concentrate stress. It also contrasts V-shaped, buttress and square threads and associates square and modified buttress forms with more favorable stress patterns in the examples presented. Such relationships should not be interpreted as proving that a particular thread design is clinically superior in every situation. [6]

A force acting at a distance from the relevant fulcrum generates a bending moment, represented in the slides as $M = F \times d$. Thus, increasing cantilever length increases the moment for a given applied force. The resulting bending may overload the abutment screw, implant and surrounding structures. Crown height, wide occlusal tables and off-axis contacts may similarly magnify unfavorable mechanical effects. [6,10]

SCREW JOINT MECHANICS

Torque, elongation, preload and clamping force

The screw joint is formed when components such as an abutment and implant are drawn together by a tightened screw. Applied rotational torque elongates the screw elastically. The internal tensile force created by this elongation is preload; elastic recovery then develops a clamping force across the joint. When clamping force remains greater than joint-separating force, the assembly is more likely to remain stable. If separating forces overcome clamping, micromovement and loosening may occur. [10]

Preload is not identical to the torque applied by the clinician. The source slides indicate that a substantial proportion of tightening torque is dissipated in friction at the threads and contacting surfaces; one slide gives approximately 90% as an illustrative value. This figure should not be treated as universal across implant systems, coatings or lubrication conditions. The presentation also describes a desirable preload as a fraction of the screw material's yield strength, underscoring the balance between sufficient elastic tension and permanent deformation. [1,7,10]

Friction and the settling effect

Friction depends on surface texture, thread contact, the undersurface of the screw head and the implant–abutment interface. It affects how efficiently applied torque produces screw tension. After tightening, microscopic surface irregularities may flatten as components settle into closer contact. This embedment relaxation decreases screw elongation and can reduce preload even without obvious external displacement. [1,7]

The slides describe early preload reduction from settling and recommend a second tightening after approximately 5–10 minutes, using the implant manufacturer's specified torque. This recommendation is consistent with the presentation's focus on minimizing early torque loss; the appropriate protocol remains system-specific. [1,10]

Screw material and mechanical strength

Screw design, yield strength, elastic modulus and fatigue resistance influence joint durability. A screw must sustain elastic elongation while resisting permanent deformation under tightening and functional loading. The presentation compares gold,

palladium and titanium-alloy screws and describes differences in counterclockwise rotation and deformation after loading. However, some experimental comparisons in the slides lack a fully identifiable matching reference, so their numeric results are not reproduced as definitive evidence here. [4,7,10]

IMPLANT CONNECTION DESIGN AND PROSTHETIC CONFIGURATION

The presentation discusses external hexagonal, internal hexagonal and conical or Morse-taper connections. Antirotational features can resist rotational displacement, particularly in single-tooth restorations. Internal and conical interfaces are described as potentially improving stability and load transfer, while external configurations may permit more micromovement in some comparisons. These trends depend on system geometry and should not be generalized to all commercial implants. [3,6,10]

Screw-retained and cement-retained restorations differ in retrievability and management of mechanical complications. A loose abutment screw beneath a cement-retained crown may be more difficult to access without damaging the restoration. The presentation also highlights the effects of implant angulation, framework passivity, splinting and occlusal design on the separating forces acting at the screw joint. [2,8,10,11]

BIOMECHANICAL COMPLICATIONS

Screw loosening

Screw loosening occurs when effective preload and clamping force decline sufficiently for functional forces to produce joint movement. The slides describe excessive loading, cantilever effects, increased crown height, bruxism, incorrect torque, material properties and unfavorable connection geometry as contributors. Loosening may further promote instability and can create an interface in which microbial contamination is possible. [3,10]

The presentation provides several complication percentages for single crowns, multiunit prostheses and overdentures. Because those individual figures are not mapped unambiguously to a specific study and denominator in the slides, they have not been repeated as independently validated incidence estimates in this manuscript.

Screw fracture

Screw fracture may follow prolonged cyclic loading, fatigue or permanent deformation, particularly when an already loose component remains in function. The presentation relates fracture susceptibility to screw diameter, material strength and repeated biomechanical stress. Early recognition and treatment of loosening are therefore important to avoid continued loading of an unstable assembly. [4,6,10]

PREVENTION AND CLINICAL MANAGEMENT

Prevention requires both maximizing appropriate clamping force and minimizing separating forces. The slides recommend limiting cantilever length, reducing excessively wide occlusal tables and steep cusp inclines, centralizing contacts where possible, avoiding unfavorable excursive contacts and evaluating parafunctional loading. Implant placement and prosthesis design should seek to align forces more favorably with the implant axis. [6,10]

Torque should be applied with a calibrated mechanical instrument according to the implant manufacturer’s instructions, rather than assuming that one numerical torque value suits every system. The presentation mentions a broad manufacturer-dependent range and a retightening interval of about 5–10 minutes to address settling. For multiunit prostheses, screws should be tightened progressively in an appropriate sequence to avoid disproportionate stress arising from nonpassive fit. [1,10]

If a screw is found to be mobile, the presentation recommends prompt assessment and treatment. Evaluation should address occlusion, prosthesis fit, screw integrity, connection geometry and any recurrent factors that may have reduced preload. Repeated loosening calls for correction of its mechanical causes, not simply repeated tightening. [3,10]

DISCUSSION

The material reviewed presents implant screw performance as a balance between preload-generated clamping force and forces tending to separate the joint. Torque alone cannot guarantee stability because friction, settling, elastic limits and functional loading modify the outcome. Likewise, implant diameter, thread geometry and connection type influence load transmission but cannot compensate for unfavorable occlusal or prosthetic design. [1,3,6,10]

The most consistent practical themes are use of system-specific torque protocols, attention to embedment relaxation, control of cantilever and oblique loading, and timely treatment of loose screws. These are principles derived from the supplied presentation and its cited literature rather than recommendations established through a new systematic assessment. [1,6,10]

LIMITATIONS


This manuscript is a narrative review restricted to one educational slide deck and its listed references. It does not include a systematic search strategy, formal risk-of-bias assessment or independent verification of every numerical claim. Several illustrations and comparative statements in the presentation lack explicit original-source attribution. Accordingly, the manuscript does not claim quantitative synthesis, comparative effectiveness or evidence grading.

CONCLUSION

Implant screw-joint stability depends on the generation and preservation of adequate preload, the frictional and elastic behavior of screw components, and the reduction of forces that tend to separate the joint. Settling, nonaxial loading, cantilevers, material fatigue and prosthetic misfit can contribute to loosening and fracture. Appropriate manufacturer-specified tightening, considered prosthetic design and prompt intervention for loosened components are central preventive measures described in the source presentation.

REFERENCES

1. Winkler S, Ring K, Ring JD, Boberick KG. Implant screw mechanics and the settling effect: an overview. Journal of oral implantology. 2003 Oct 1;29(5):242-5.
2. Kim WD, Jacobson Z, Nathanson D. In vitro stress analyses of dental implants supporting screw-retained and cement-retained prostheses. Implant dentistry. 1999 Jan 1;8(2):141-51.
3. Huang Y, Wang J. Mechanism of and factors associated with the loosening of the implant abutment screw: a review. Journal of Esthetic and Restorative Dentistry. 2019 Jul;31(4):338-45.
4. Yousef H, Luke A, Ricci J, Weiner S. Analysis of changes in implant screws subject to occlusal loading: a preliminary analysis. Implant dentistry. 2005 Dec 1;14(4):378-85.
5. Morneburg TR, Pröschel PA. In vivo forces on implants influenced by occlusal scheme and food consistency. International Journal of Prosthodontics. 2003 Sep 1;16(5).
6. Şahin S, Cehreli MC, Yalçın E. The influence of functional forces on the biomechanics of implant-supported prostheses—a review. Journal of dentistry. 2002 Sep 1;30(7-8):271-82.
7. Park JK, Choi JU, Jeon YC, Choi KS, Jeong CM. Effects of abutment screw coating on implant preload. Journal of Prosthodontics: Implant, Esthetic and Reconstructive Dentistry. 2010 Aug;19(6):458-64.
8. Lemos CA, de Souza Batista VE, de Faria Almeida DA, Júnior JF, Verri FR, Pellizzer EP. Evaluation of cement-retained versus screw-retained implant-supported restorations for marginal bone loss: A systematic review and meta-analysis. The Journal of prosthetic dentistry. 2016 Apr 1;115(4):419-27.
9. McGlumphy EA, Elfers CL, Mendel DA: Optimum torque values for implant abutment screws. J Dent Res 72:191, 1993.
10. McGlumphy EA, Mendel DA, Holloway JA. Implant screw mechanics. Dental Clinics of North America. 1998 Jan 1;42(1):71-89.
11. Hebel KS, Gajjar RC. Cement-retained versus screw-retained implant restorations: achieving optimal occlusion and esthetics in implant dentistry. The Journal of prosthetic dentistry. 1997 Jan 1;77(1):28-35.
12. Albayrak H, Gumus HO, Tasdemir Z. Does abutment preparation affect abutment screw joint stability? An in vitro study. The Journal of Prosthetic Dentistry. 2021 Mar 1;125(3):500-e1.



• **Fig. 1:** Diagrams of Force Transmission by Different Implant Thread Types. (A) V-thread: the direction of forces applied by V-form screw threads. (B) Buttress thread: the direction of forces applied by buttress-form screw threads. (C) Square thread: the direction of forces applied by square-form threads. *(Image courtesy of Glidewell Dental, Newport*

Figure 1: Thread profiles and directions of force transmission (reproduced from supplied presentation, slide 16; original image attribution and reuse permission require verification before journal publication).